











































| Number | Name | colour | Opacity | Lightfastness | Pigments | R | G | B | L | a | b | H | V | C |
|--------|------------------------------|---|---------|---------------|----------------------|-----|-----|-----|------|-------|-------|-------|-----|------|
| 722 | Winsor lemon |  | T | A | PY3 | 245 | 213 | 0 | 87.4 | -6.5 | 97.9 | 5.2Y | 8.6 | 11.3 |
| 086 | Cadmium lemon |  | O | A | PY35 | 255 | 216 | 0 | 89.4 | -5.0 | 101 | 5.2Y | 8.8 | 13.7 |
| 730 | Winsor yellow |  | T | A | PY74 | 255 | 193 | 0 | 84.8 | 6.6 | 110 | 2.9Y | 8.3 | 11.8 |
| 113 | Cadmium yellow light |  | O | A | PY35 | 255 | 190 | 0 | 84.6 | 9.3 | 112 | 2.0Y | 8.3 | 14.0 |
| 116 | Cadmium yellow medium |  | O | A | PY35 | 255 | 164 | 0 | 79.3 | 27.6 | 93.0 | 7.5YR | 7.8 | 15.0 |
| 111 | Cadmium yellow deep |  | O | A | PY35 - PO20 | 255 | 144 | 0 | 75.1 | 38.2 | 84.9 | 4.6YR | 7.4 | 15.4 |
| 089 | Cadmium orange |  | O | A | PR108 - PO20 | 254 | 97 | 0 | 64.8 | 58.2 | 96.4 | 0.4YR | 6.2 | 16.3 |
| 257 | Flesh tint |  | O | A | PY42 - PW6 - PV19 | 219 | 129 | 122 | 64.9 | 38.2 | 21.3 | 5.7R | 6.3 | 9.3 |
| 100 | Cadmium red light |  | O | A | PR108 | 222 | 52 | 0 | 52.7 | 68.8 | 68.0 | 8.9R | 5.1 | 17.7 |
| 099 | Cadmium red medium |  | O | A | PR108 | 201 | 23 | 8 | 46.1 | 71.5 | 59.2 | 8.4R | 4.6 | 17.6 |
| 726 | Winsor red |  | T | A | PR188 - PR170 | 213 | 44 | 32 | 50.1 | 69.8 | 54.1 | 7.7R | 4.9 | 17.3 |
| 097 | Cadmium red deep |  | O | A | PR108 | 141 | 37 | 45 | 34.3 | 52.0 | 25.3 | 6.0R | 3.4 | 10.9 |
| 501 | Permanent rose |  | T | A | PV19 | 165 | 35 | 54 | 39.1 | 59.5 | 27.9 | 4.9R | 3.8 | 13.3 |
| 468 | Permanent alizarin crimson |  | T | A | PR177 | 96 | 0 | 13 | 19.2 | 49.8 | 25.3 | 0.1YR | 2.1 | 9.9 |
| 380 | Magenta |  | T | A | PR122 - PB15 | 114 | 6 | 52 | 25.1 | 50.5 | 9.1 | 2.3R | 2.6 | 9.3 |
| 229 | Dioxazine purple |  | T | A | PV23 | 39 | 35 | 49 | 14.2 | 6.5 | -8.2 | 1.0P | 1.3 | 1.6 |
| 263 | French ultramarine |  | T | A | PB29 | 0 | 55 | 180 | 19.7 | 44.5 | -84.2 | 7.3PB | 2.5 | 19.5 |
| 178 | Cobalt blue |  | T | A | PB28 | 33 | 68 | 125 | 26.3 | 12.3 | -40.2 | 5.9PB | 2.6 | 9.0 |
| 538 | Prussian blue |  | T | A | PB27 | 25 | 28 | 35 | 9.8 | 0.7 | -5.6 | 4.8PB | 0.9 | 1.0 |
| 514 | Phthalo blue |  | T | A | PB15 | 0 | 39 | 80 | 12.2 | 11.1 | -35.1 | 6.2PB | 1.2 | 7.9 |
| 137 | Cerulean blue |  | O | AA | PB35 | 0 | 105 | 150 | 37.0 | -14.1 | -39.5 | 0.1PB | 3.6 | 9.8 |
| 522 | Phthalo green |  | T | A | PG7 | 0 | 85 | 53 | 26.2 | -55.3 | 0.2 | 8.0G | 2.8 | 5.5 |
| 692 | Viridian |  | T | AA | PG18 | 0 | 71 | 41 | 22.4 | -47.7 | 4.6 | 4.7G | 2.4 | 6.0 |
| 521 | Phthalo green (yellow shade) |  | T | A | PG36 | 12 | 55 | 44 | 19.0 | -16.5 | 0.0 | 1.1BG | 1.8 | 3.7 |
| 637 | Terre verte |  | O | AA | PG7 - PG23 | 91 | 147 | 108 | 56.0 | -30.7 | 12.7 | 3.7G | 5.4 | 5.8 |
| 459 | Oxide of chromium |  | O | AA | PG17 | 66 | 97 | 52 | 38.1 | -24.7 | 23.1 | 9.0GY | 3.7 | 5.4 |
| 503 | Permanent sap green |  | T | A | PG7 - PY129 | 34 | 41 | 24 | 15.8 | -9.1 | 10.8 | 6.7GY | 1.5 | 2.7 |
| 447 | Olive green |  | T | B | PY129 - PBk7 | 37 | 41 | 30 | 15.8 | -4.1 | 6.2 | 4.6GY | 1.5 | 1.6 |
| 422 | Naples yellow hue |  | O | A | PW6 - PR101 - PY42 | 224 | 171 | 114 | 75.3 | 12.1 | 38.6 | 7.9YR | 7.4 | 6.1 |
| 744 | Yellow ochre |  | O | AA | PY43 | 189 | 118 | 53 | 58.2 | 21.7 | 49.0 | 6.5YR | 5.7 | 8.6 |
| 552 | Raw sienna |  | T | AA | PY43 | 212 | 125 | 0 | 63.1 | 26.3 | 72.6 | 6.1YR | 6.1 | 11.9 |
| 074 | Burnt sienna |  | T | AA | PR101 | 99 | 58 | 47 | 30.0 | 19.2 | 16.3 | 1.3YR | 2.9 | 4.4 |
| 362 | Light red |  | O | AA | PR101 | 142 | 56 | 33 | 37.3 | 37.9 | 35.3 | 10R | 3.6 | 9.4 |
| 317 | Indian red |  | O | AA | PR101 | 123 | 60 | 55 | 34.6 | 29.7 | 18.3 | 7.8R | 3.4 | 6.4 |
| 076 | Burnt umber |  | T | AA | PBr7 | 65 | 48 | 43 | 21.9 | 8.3 | 7.0 | 2.8YR | 2.1 | 1.9 |
| 554 | Raw umber |  | T | AA | PBr7 - PBk11 | 69 | 50 | 36 | 23.0 | 7.7 | 13.1 | 7.3YR | 2.2 | 2.6 |
| 217 | Davy's grey |  | T | A | PPBk19 - PY42 - PBk7 | 62 | 61 | 55 | 25.7 | -0.8 | 4.2 | 8.0Y | 2.5 | 0.6 |
| 465 | Payne's grey |  | O | A | PB29 | 12 | 28 | 43 | 8.4 | 0.3 | -13.9 | 3.8PB | 0.8 | 2.4 |
| 331 | Ivory black |  | O | AA | PBk9 | 44 | 45 | 47 | 18.3 | -0.1 | -1.1 | 2.7PB | 1.8 | 0.2 |
| 337 | Lamp black |  | O | AA | PBk6 | 27 | 27 | 27 | 9.6 | 0.3 | -0.2 | N | 0.9 | 0.0 |
| 415 | Mixing white |  | O | AA | PW6 | 243 | 235 | 222 | 93.6 | 0.7 | 7.2 | 0.2Y | 9.3 | 1.0 |
| 644 | Titanium white |  | O | AA | PW6 | 239 | 238 | 232 | 94.0 | -0.4 | 2.8 | 5.0Y | 9.3 | 0.4 |

Colours scanned and pasted in from patch samples. Colour values measured using ColorMunki® and converted to Munsell using BabelColor CT&A.

Note that all colour values are approximate, and conversions are even more approximate, particularly to the Munsell System.











































| Number | Name | colour | Opacity | Lightfastness | Pigments | R | G | B | L | a | b | H | V | C |
|--------|------------------------------|--------|---------|---------------|----------------------|-----|-----|-----|------|-------|-------|-------|-----|------|
| 074 | Burnt sienna | | T | AA | PR101 | 99 | 58 | 47 | 30.0 | 19.2 | 16.3 | 1.3YR | 2.9 | 4.4 |
| 076 | Burnt umber | | T | AA | PBr7 | 65 | 48 | 43 | 21.9 | 8.3 | 7.0 | 2.8YR | 2.1 | 1.9 |
| 086 | Cadmium lemon | | O | A | PY35 | 255 | 216 | 0 | 89.4 | -5.0 | 101 | 5.2Y | 8.8 | 13.7 |
| 089 | Cadmium orange | | O | A | PR108 - PO20 | 254 | 97 | 0 | 64.8 | 58.2 | 96.4 | 0.4YR | 6.2 | 16.3 |
| 097 | Cadmium red deep | | O | A | PR108 | 141 | 37 | 45 | 34.3 | 52.0 | 25.3 | 6.0R | 3.4 | 10.9 |
| 099 | Cadmium red medium | | O | A | PR108 | 201 | 23 | 8 | 46.1 | 71.5 | 59.2 | 8.4R | 4.6 | 17.6 |
| 100 | Cadmium red light | | O | A | PR108 | 222 | 52 | 0 | 52.7 | 68.8 | 68.0 | 8.9R | 5.1 | 17.7 |
| 111 | Cadmium yellow deep | | O | A | PY35 - PO20 | 255 | 144 | 0 | 75.1 | 38.2 | 84.9 | 4.6YR | 7.4 | 15.4 |
| 113 | Cadmium yellow light | | O | A | PY35 | 255 | 190 | 0 | 84.6 | 9.3 | 112 | 2.0Y | 8.3 | 14.0 |
| 116 | Cadmium yellow medium | | O | A | PY35 | 255 | 164 | 0 | 79.3 | 27.6 | 93.0 | 7.5YR | 7.8 | 15.0 |
| 137 | Cerulean blue | | O | AA | PB35 | 0 | 105 | 150 | 37.0 | -14.1 | -39.5 | 0.1PB | 3.6 | 9.8 |
| 178 | Cobalt blue | | T | A | PB28 | 33 | 68 | 125 | 26.3 | 12.3 | -40.2 | 5.9PB | 2.6 | 9.0 |
| 217 | Davy's grey | | T | A | PPBk19 - PY42 - PBk7 | 62 | 61 | 55 | 25.7 | -0.8 | 4.2 | 8.0Y | 2.5 | 0.6 |
| 229 | Dioxazine purple | | T | A | PV23 | 39 | 35 | 49 | 14.2 | 6.5 | -8.2 | 1.0P | 1.3 | 1.6 |
| 257 | Flesh tint | | O | A | PY42 - PW6 - PV19 | 219 | 129 | 122 | 64.9 | 38.2 | 21.3 | 5.7R | 6.3 | 9.3 |
| 263 | French ultramarine | | T | A | PB29 | 0 | 55 | 180 | 19.7 | 44.5 | -84.2 | 7.3PB | 2.5 | 19.5 |
| 317 | Indian red | | O | AA | PR101 | 123 | 60 | 55 | 34.6 | 29.7 | 18.3 | 7.8R | 3.4 | 6.4 |
| 331 | Ivory black | | O | AA | PBk9 | 44 | 45 | 47 | 18.3 | -0.1 | -1.1 | 2.7PB | 1.8 | 0.2 |
| 337 | Lamp black | | O | AA | PBk6 | 27 | 27 | 27 | 9.6 | 0.3 | -0.2 | N | 0.9 | 0.0 |
| 362 | Light red | | O | AA | PR101 | 142 | 56 | 33 | 37.3 | 37.9 | 35.3 | 10R | 3.6 | 9.4 |
| 380 | Magenta | | T | A | PR122 - PB15 | 114 | 6 | 52 | 25.1 | 50.5 | 9.1 | 2.3R | 2.6 | 9.3 |
| 415 | Mixing white | | O | AA | PW6 | 243 | 235 | 222 | 93.6 | 0.7 | 7.2 | 0.2Y | 9.3 | 1.0 |
| 422 | Naples yellow hue | | O | A | PW6 - PR101 - PY42 | 224 | 171 | 114 | 75.3 | 12.1 | 38.6 | 7.9YR | 7.4 | 6.1 |
| 447 | Olive green | | T | B | PY129 - PBk7 | 37 | 41 | 30 | 15.8 | -4.1 | 6.2 | 4.6GY | 1.5 | 1.6 |
| 459 | Oxide of chromium | | O | AA | PG17 | 66 | 97 | 52 | 38.1 | -24.7 | 23.1 | 9.0GY | 3.7 | 5.4 |
| 465 | Payne's grey | | O | A | PB29 | 12 | 28 | 43 | 8.4 | 0.3 | -13.9 | 3.8PB | 0.8 | 2.4 |
| 468 | Permanent alizarin crimson | | T | A | PR177 | 96 | 0 | 13 | 19.2 | 49.8 | 25.3 | 0.1YR | 2.1 | 9.9 |
| 501 | Permanent rose | | T | A | PV19 | 165 | 35 | 54 | 39.1 | 59.5 | 27.9 | 4.9R | 3.8 | 13.3 |
| 503 | Permanent sap green | | T | A | PG7 - PY129 | 34 | 41 | 24 | 15.8 | -9.1 | 10.8 | 6.7GY | 1.5 | 2.7 |
| 514 | Phthalo blue | | T | A | PB15 | 0 | 39 | 80 | 12.2 | 11.1 | -35.1 | 6.2PB | 1.2 | 7.9 |
| 521 | Phthalo green (yellow shade) | | T | A | PG36 | 12 | 55 | 44 | 19.0 | -16.5 | 0.0 | 1.1BG | 1.8 | 3.7 |
| 522 | Phthalo green | | T | A | PG7 | 0 | 85 | 53 | 26.2 | -55.3 | 0.2 | 8.0G | 2.8 | 5.5 |
| 538 | Prussian blue | | T | A | PB27 | 25 | 28 | 35 | 9.8 | 0.7 | -5.6 | 4.8PB | 0.9 | 1.0 |
| 552 | Raw sienna | | T | AA | PY43 | 212 | 125 | 0 | 63.1 | 26.3 | 72.6 | 6.1YR | 6.1 | 11.9 |
| 554 | Raw umber | | T | AA | PBr7 - PBk11 | 69 | 50 | 36 | 23.0 | 7.7 | 13.1 | 7.3YR | 2.2 | 2.6 |
| 637 | Terre verte | | O | AA | PG7 - PG23 | 91 | 147 | 108 | 56.0 | -30.7 | 12.7 | 3.7G | 5.4 | 5.8 |
| 644 | Titanium white | | O | AA | PW6 | 239 | 238 | 232 | 94.0 | -0.4 | 2.8 | 5.0Y | 9.3 | 0.4 |
| 692 | Viridian | | T | AA | PG18 | 0 | 71 | 41 | 22.4 | -47.7 | 4.6 | 4.7G | 2.4 | 6.0 |
| 722 | Winsor lemon | | T | A | PY3 | 245 | 213 | 0 | 87.4 | -6.5 | 97.9 | 5.2Y | 8.6 | 11.3 |
| 726 | Winsor red | | T | A | PR188 - PR170 | 213 | 44 | 32 | 50.1 | 69.8 | 54.1 | 7.7R | 4.9 | 17.3 |
| 730 | Winsor yellow | | T | A | PY74 | 255 | 193 | 0 | 84.8 | 6.6 | 110 | 2.9Y | 8.3 | 11.8 |
| 744 | Yellow ochre | | O | AA | PY43 | 189 | 118 | 53 | 58.2 | 21.7 | 49.0 | 6.5YR | 5.7 | 8.6 |

© 2009 EHN & DIJ Oakley

All commercial rights reserved: contact h.oakley@btconnect.com for permission to use in any commercial situation.











































Colours scanned and pasted in from patch samples. Colour values measured using ColorMunki® and converted to Munsell using BabelColor CT&A.

Note that all colour values are approximate, and conversions are even more approximate, particularly to the Munsell System.

| Number | Name | colour | Opacity | Lightfastness | Pigments | R | G | B | L | a | b | H | V | C |
|--------|------------------------------|---|---------|---------------|----------------------|-----|-----|-----|------|-------|-------|-------|-----|------|
| 086 | Cadmium lemon |  | O | A | PY35 | 255 | 216 | 0 | 89.4 | -5.0 | 101 | 5.2Y | 8.8 | 13.7 |
| 113 | Cadmium yellow light |  | O | A | PY35 | 255 | 190 | 0 | 84.6 | 9.3 | 112 | 2.0Y | 8.3 | 14.0 |
| 116 | Cadmium yellow medium |  | O | A | PY35 | 255 | 164 | 0 | 79.3 | 27.6 | 93.0 | 7.5YR | 7.8 | 15.0 |
| 111 | Cadmium yellow deep |  | O | A | PY35 - PO20 | 255 | 144 | 0 | 75.1 | 38.2 | 84.9 | 4.6YR | 7.4 | 15.4 |
| 089 | Cadmium orange |  | O | A | PR108 - PO20 | 254 | 97 | 0 | 64.8 | 58.2 | 96.4 | 0.4YR | 6.2 | 16.3 |
| 257 | Flesh tint |  | O | A | PY42 - PW6 - PV19 | 219 | 129 | 122 | 64.9 | 38.2 | 21.3 | 5.7R | 6.3 | 9.3 |
| 100 | Cadmium red light |  | O | A | PR108 | 222 | 52 | 0 | 52.7 | 68.8 | 68.0 | 8.9R | 5.1 | 17.7 |
| 099 | Cadmium red medium |  | O | A | PR108 | 201 | 23 | 8 | 46.1 | 71.5 | 59.2 | 8.4R | 4.6 | 17.6 |
| 097 | Cadmium red deep |  | O | A | PR108 | 141 | 37 | 45 | 34.3 | 52.0 | 25.3 | 6.0R | 3.4 | 10.9 |
| 137 | Cerulean blue |  | O | AA | PB35 | 0 | 105 | 150 | 37.0 | -14.1 | -39.5 | 0.1PB | 3.6 | 9.8 |
| 637 | Terre verte |  | O | AA | PG7 - PG23 | 91 | 147 | 108 | 56.0 | -30.7 | 12.7 | 3.7G | 5.4 | 5.8 |
| 459 | Oxide of chromium |  | O | AA | PG17 | 66 | 97 | 52 | 38.1 | -24.7 | 23.1 | 9.0GY | 3.7 | 5.4 |
| 422 | Naples yellow hue |  | O | A | PW6 - PR101 - PY42 | 224 | 171 | 114 | 75.3 | 12.1 | 38.6 | 7.9YR | 7.4 | 6.1 |
| 744 | Yellow ochre |  | O | AA | PY43 | 189 | 118 | 53 | 58.2 | 21.7 | 49.0 | 6.5YR | 5.7 | 8.6 |
| 362 | Light red |  | O | AA | PR101 | 142 | 56 | 33 | 37.3 | 37.9 | 35.3 | 10R | 3.6 | 9.4 |
| 317 | Indian red |  | O | AA | PR101 | 123 | 60 | 55 | 34.6 | 29.7 | 18.3 | 7.8R | 3.4 | 6.4 |
| 465 | Payne's grey |  | O | A | PB29 | 12 | 28 | 43 | 8.4 | 0.3 | -13.9 | 3.8PB | 0.8 | 2.4 |
| 331 | Ivory black |  | O | AA | PBk9 | 44 | 45 | 47 | 18.3 | -0.1 | -1.1 | 2.7PB | 1.8 | 0.2 |
| 337 | Lamp black |  | O | AA | PBk6 | 27 | 27 | 27 | 9.6 | 0.3 | -0.2 | N | 0.9 | 0.0 |
| 415 | Mixing white |  | O | AA | PW6 | 243 | 235 | 222 | 93.6 | 0.7 | 7.2 | 0.2Y | 9.3 | 1.0 |
| 644 | Titanium white |  | O | AA | PW6 | 239 | 238 | 232 | 94.0 | -0.4 | 2.8 | 5.0Y | 9.3 | 0.4 |
| 722 | Winsor lemon |  | T | A | PY3 | 245 | 213 | 0 | 87.4 | -6.5 | 97.9 | 5.2Y | 8.6 | 11.3 |
| 730 | Winsor yellow |  | T | A | PY74 | 255 | 193 | 0 | 84.8 | 6.6 | 110 | 2.9Y | 8.3 | 11.8 |
| 726 | Winsor red |  | T | A | PR188 - PR170 | 213 | 44 | 32 | 50.1 | 69.8 | 54.1 | 7.7R | 4.9 | 17.3 |
| 501 | Permanent rose |  | T | A | PV19 | 165 | 35 | 54 | 39.1 | 59.5 | 27.9 | 4.9R | 3.8 | 13.3 |
| 468 | Permanent alizarin crimson |  | T | A | PR177 | 96 | 0 | 13 | 19.2 | 49.8 | 25.3 | 0.1YR | 2.1 | 9.9 |
| 380 | Magenta |  | T | A | PR122 - PB15 | 114 | 6 | 52 | 25.1 | 50.5 | 9.1 | 2.3R | 2.6 | 9.3 |
| 229 | Dioxazine purple |  | T | A | PV23 | 39 | 35 | 49 | 14.2 | 6.5 | -8.2 | 1.0P | 1.3 | 1.6 |
| 263 | French ultramarine |  | T | A | PB29 | 0 | 55 | 180 | 19.7 | 44.5 | -84.2 | 7.3PB | 2.5 | 19.5 |
| 178 | Cobalt blue |  | T | A | PB28 | 33 | 68 | 125 | 26.3 | 12.3 | -40.2 | 5.9PB | 2.6 | 9.0 |
| 538 | Prussian blue |  | T | A | PB27 | 25 | 28 | 35 | 9.8 | 0.7 | -5.6 | 4.8PB | 0.9 | 1.0 |
| 514 | Phthalo blue |  | T | A | PB15 | 0 | 39 | 80 | 12.2 | 11.1 | -35.1 | 6.2PB | 1.2 | 7.9 |
| 522 | Phthalo green |  | T | A | PG7 | 0 | 85 | 53 | 26.2 | -55.3 | 0.2 | 8.0G | 2.8 | 5.5 |
| 692 | Viridian |  | T | AA | PG18 | 0 | 71 | 41 | 22.4 | -47.7 | 4.6 | 4.7G | 2.4 | 6.0 |
| 521 | Phthalo green (yellow shade) |  | T | A | PG36 | 12 | 55 | 44 | 19.0 | -16.5 | 0.0 | 1.1BG | 1.8 | 3.7 |
| 503 | Permanent sap green |  | T | A | PG7 - PY129 | 34 | 41 | 24 | 15.8 | -9.1 | 10.8 | 6.7GY | 1.5 | 2.7 |
| 447 | Olive green |  | T | B | PY129 - PBk7 | 37 | 41 | 30 | 15.8 | -4.1 | 6.2 | 4.6GY | 1.5 | 1.6 |
| 552 | Raw sienna |  | T | AA | PY43 | 212 | 125 | 0 | 63.1 | 26.3 | 72.6 | 6.1YR | 6.1 | 11.9 |
| 074 | Burnt sienna |  | T | AA | PR101 | 99 | 58 | 47 | 30.0 | 19.2 | 16.3 | 1.3YR | 2.9 | 4.4 |
| 076 | Burnt umber |  | T | AA | PBr7 | 65 | 48 | 43 | 21.9 | 8.3 | 7.0 | 2.8YR | 2.1 | 1.9 |
| 554 | Raw umber |  | T | AA | PBr7 - PBk11 | 69 | 50 | 36 | 23.0 | 7.7 | 13.1 | 7.3YR | 2.2 | 2.6 |
| 217 | Davy's grey |  | T | A | PPBk19 - PY42 - PBk7 | 62 | 61 | 55 | 25.7 | -0.8 | 4.2 | 8.0Y | 2.5 | 0.6 |

Colours scanned and pasted in from patch samples. Colour values measured using ColorMunki® and converted to Munsell using BabelColor CT&A.

Note that all colour values are approximate, and conversions are even more approximate, particularly to the Munsell System.

| Number | Name | colour | Opacity | Lightfastness | Pigments | R | G | B | L | a | b | H | V | C |
|--------|------------------------------|---|---------|---------------|----------------------|-----|-----|-----|------|-------|-------|-------|-----|------|
| 074 | Burnt sienna |  | T | AA | PR101 | 99 | 58 | 47 | 30.0 | 19.2 | 16.3 | 1.3YR | 2.9 | 4.4 |
| 076 | Burnt umber |  | T | AA | PBr7 | 65 | 48 | 43 | 21.9 | 8.3 | 7.0 | 2.8YR | 2.1 | 1.9 |
| 086 | Cadmium lemon |  | O | A | PY35 | 255 | 216 | 0 | 89.4 | -5.0 | 101 | 5.2Y | 8.8 | 13.7 |
| 089 | Cadmium orange |  | O | A | PR108 - PO20 | 254 | 97 | 0 | 64.8 | 58.2 | 96.4 | 0.4YR | 6.2 | 16.3 |
| 097 | Cadmium red deep |  | O | A | PR108 | 141 | 37 | 45 | 34.3 | 52.0 | 25.3 | 6.0R | 3.4 | 10.9 |
| 100 | Cadmium red light |  | O | A | PR108 | 222 | 52 | 0 | 52.7 | 68.8 | 68.0 | 8.9R | 5.1 | 17.7 |
| 099 | Cadmium red medium |  | O | A | PR108 | 201 | 23 | 8 | 46.1 | 71.5 | 59.2 | 8.4R | 4.6 | 17.6 |
| 111 | Cadmium yellow deep |  | O | A | PY35 - PO20 | 255 | 144 | 0 | 75.1 | 38.2 | 84.9 | 4.6YR | 7.4 | 15.4 |
| 113 | Cadmium yellow light |  | O | A | PY35 | 255 | 190 | 0 | 84.6 | 9.3 | 112 | 2.0Y | 8.3 | 14.0 |
| 116 | Cadmium yellow medium |  | O | A | PY35 | 255 | 164 | 0 | 79.3 | 27.6 | 93.0 | 7.5YR | 7.8 | 15.0 |
| 137 | Cerulean blue |  | O | AA | PB35 | 0 | 105 | 150 | 37.0 | -14.1 | -39.5 | 0.1PB | 3.6 | 9.8 |
| 178 | Cobalt blue |  | T | A | PB28 | 33 | 68 | 125 | 26.3 | 12.3 | -40.2 | 5.9PB | 2.6 | 9.0 |
| 217 | Davy's grey |  | T | A | PPBk19 - PY42 - PBk7 | 62 | 61 | 55 | 25.7 | -0.8 | 4.2 | 8.0Y | 2.5 | 0.6 |
| 229 | Dioxazine purple |  | T | A | PV23 | 39 | 35 | 49 | 14.2 | 6.5 | -8.2 | 1.0P | 1.3 | 1.6 |
| 257 | Flesh tint |  | O | A | PY42 - PW6 - PV19 | 219 | 129 | 122 | 64.9 | 38.2 | 21.3 | 5.7R | 6.3 | 9.3 |
| 263 | French ultramarine |  | T | A | PB29 | 0 | 55 | 180 | 19.7 | 44.5 | -84.2 | 7.3PB | 2.5 | 19.5 |
| 317 | Indian red |  | O | AA | PR101 | 123 | 60 | 55 | 34.6 | 29.7 | 18.3 | 7.8R | 3.4 | 6.4 |
| 331 | Ivory black |  | O | AA | PBk9 | 44 | 45 | 47 | 18.3 | -0.1 | -1.1 | 2.7PB | 1.8 | 0.2 |
| 337 | Lamp black |  | O | AA | PBk6 | 27 | 27 | 27 | 9.6 | 0.3 | -0.2 | N | 0.9 | 0.0 |
| 362 | Light red |  | O | AA | PR101 | 142 | 56 | 33 | 37.3 | 37.9 | 35.3 | 10R | 3.6 | 9.4 |
| 380 | Magenta |  | T | A | PR122 - PB15 | 114 | 6 | 52 | 25.1 | 50.5 | 9.1 | 2.3R | 2.6 | 9.3 |
| 415 | Mixing white |  | O | AA | PW6 | 243 | 235 | 222 | 93.6 | 0.7 | 7.2 | 0.2Y | 9.3 | 1.0 |
| 422 | Naples yellow hue |  | O | A | PW6 - PR101 - PY42 | 224 | 171 | 114 | 75.3 | 12.1 | 38.6 | 7.9YR | 7.4 | 6.1 |
| 447 | Olive green |  | T | B | PY129 - PBk7 | 37 | 41 | 30 | 15.8 | -4.1 | 6.2 | 4.6GY | 1.5 | 1.6 |
| 459 | Oxide of chromium |  | O | AA | PG17 | 66 | 97 | 52 | 38.1 | -24.7 | 23.1 | 9.0GY | 3.7 | 5.4 |
| 465 | Payne's grey |  | O | A | PB29 | 12 | 28 | 43 | 8.4 | 0.3 | -13.9 | 3.8PB | 0.8 | 2.4 |
| 468 | Permanent alizarin crimson |  | T | A | PR177 | 96 | 0 | 13 | 19.2 | 49.8 | 25.3 | 0.1YR | 2.1 | 9.9 |
| 501 | Permanent rose |  | T | A | PV19 | 165 | 35 | 54 | 39.1 | 59.5 | 27.9 | 4.9R | 3.8 | 13.3 |
| 503 | Permanent sap green |  | T | A | PG7 - PY129 | 34 | 41 | 24 | 15.8 | -9.1 | 10.8 | 6.7GY | 1.5 | 2.7 |
| 514 | Phthalo blue |  | T | A | PB15 | 0 | 39 | 80 | 12.2 | 11.1 | -35.1 | 6.2PB | 1.2 | 7.9 |
| 522 | Phthalo green |  | T | A | PG7 | 0 | 85 | 53 | 26.2 | -55.3 | 0.2 | 8.0G | 2.8 | 5.5 |
| 521 | Phthalo green (yellow shade) |  | T | A | PG36 | 12 | 55 | 44 | 19.0 | -16.5 | 0.0 | 1.1BG | 1.8 | 3.7 |
| 538 | Prussian blue |  | T | A | PB27 | 25 | 28 | 35 | 9.8 | 0.7 | -5.6 | 4.8PB | 0.9 | 1.0 |
| 552 | Raw sienna |  | T | AA | PY43 | 212 | 125 | 0 | 63.1 | 26.3 | 72.6 | 6.1YR | 6.1 | 11.9 |
| 554 | Raw umber |  | T | AA | PBr7 - PBk11 | 69 | 50 | 36 | 23.0 | 7.7 | 13.1 | 7.3YR | 2.2 | 2.6 |
| 637 | Terre verte |  | O | AA | PG7 - PG23 | 91 | 147 | 108 | 56.0 | -30.7 | 12.7 | 3.7G | 5.4 | 5.8 |
| 644 | Titanium white |  | O | AA | PW6 | 239 | 238 | 232 | 94.0 | -0.4 | 2.8 | 5.0Y | 9.3 | 0.4 |
| 692 | Viridian |  | T | AA | PG18 | 0 | 71 | 41 | 22.4 | -47.7 | 4.6 | 4.7G | 2.4 | 6.0 |
| 722 | Winsor lemon |  | T | A | PY3 | 245 | 213 | 0 | 87.4 | -6.5 | 97.9 | 5.2Y | 8.6 | 11.3 |
| 726 | Winsor red |  | T | A | PR188 - PR170 | 213 | 44 | 32 | 50.1 | 69.8 | 54.1 | 7.7R | 4.9 | 17.3 |
| 730 | Winsor yellow |  | T | A | PY74 | 255 | 193 | 0 | 84.8 | 6.6 | 110 | 2.9Y | 8.3 | 11.8 |
| 744 | Yellow ochre |  | O | AA | PY43 | 189 | 118 | 53 | 58.2 | 21.7 | 49.0 | 6.5YR | 5.7 | 8.6 |

Colours scanned and pasted in from patch samples. Colour values measured using ColorMunki® and converted to Munsell using BabelColor CT&A.

Note that all colour values are approximate, and conversions are even more approximate, particularly to the Munsell System.